

SPRAYTITE® COMFORT XL Series

BUILDING ENVELOPE INSULATION

Intertek CCRR-0374, ICC ESR-2642

DESCRIPTION:

SPRAYTITE COMFORT XL is a two-component closed-cell spray polyurethane foam system utilizing an EPA-approved, zero ozone-depleting blowing agent having extremely low (less than 1) global warming potential (low-GWP). It is designed for use in residential construction and common commercial insulation applications. **SPRAYTITE COMFORT XL** is compatible with most common construction materials, and the resin can only be processed with BASF Elastospay® 8000A isocyanate.

The benefits of **SPRAYTITE COMFORT XL** include:

- Superior insulation performance
- Controls moisture infiltration
- Controls air infiltration
- FEMA Class 5 flood-damage resistant rated material
- Non-fibrous
- Structural enhancement
- Speed of installation

REACTIVITIES AVAILABLE	AMBIENT TEMPERATURE RANGE
SPRAYTITE COMFORT XL W	20°F to 65°F
SPRAYTITE COMFORT XL S	60°F to 120°F

TYPICAL PROPERTIES⁽¹⁾

PROPERTY	METHOD	SPRAYTITE COMFORT XL
Resin:		
Specific Gravity @ 70°F	ASTM D 1638	1.22
Viscosity @ 70°F (cps)	Brookfield	720
Cured Foam:		
Density, (pcf) core @ 4-6" lifts	ASTM D 1622	2.00 – 2.40
Thermal Resistance		
R-value (ft ² hr °F/Btu in) ⁽²⁾	ASTM C 518	6.9 @ 1-in thick
R-value (ft ² hr °F/Btu in)	Calculated	6.8 / in @ ≥ 4-in thick
Compressive Strength (psi)	ASTM D 1621	26 ±1.5% [^]
Water Vapor (Perm Inch)	ASTM E 96	1.09
Water Vapor Transmission – Permeance (perms)	ASTM E 96	<1.0 @ 1.25" thickness (Class II vapor retarder)
Air Leakage ⁽⁵⁾ (L/s*m ² @ 75 Pa ΔP)	ASTM E 2178	Meets <0.02 @ 1.0 inch (Air impermeable)
Response to Thermal and Humid Aging (% volume change)		
158°F / 97% RH / 168 hrs	ASTM D 2126	+2.29%
Closed Cell Content (%)	ASTM D 6226	>90%

The coefficient of thermal expansion varies between 3x10⁻⁵ and 4x10⁻⁴ 1/K or 1.5x10⁻⁵ and 2x10⁻⁴ 1/°F. The lower end of the range relates to closed-cell SPF while the higher values are reported for open-cell foams.

ADDITIONAL TESTING, APPROVALS & CERTIFICATIONS:

- ASTM E 84 (Class I at 4-in thickness) ⁽³⁾ ⁽⁴⁾
- ASTM C 1029 – Type II Compliant
- INTERTEK Code Compliance Research Report CCRR-0374 (ccSPF all HFO)
- ICC Evaluation Service Report ESR-2642 (ccSPF HFC / HFO)
- Approved for Attics & Crawl Spaces Installations with and without prescriptive ignition barriers per ICC-ES AC377, Appendix A1.2.2 and Appendix X

Odor level of spray polyurethane foam is dependent on proper application using the recommended processing parameters and proper ventilation.

Please contact your local Sales or Technical Representative for specific questions regarding additional **SPRAYTITE COMFORT XL** properties, approvals, or certifications.

(1) These physical property values are typical for this material as applied at our development facility under controlled conditions. SPF performance and actual physical properties will vary with differences in application (i.e. ambient conditions, process equipment and settings, material throughput, etc). As a result, these published properties should be used as guidelines solely for the purpose of evaluation. Physical property specifications should be determined from actual production material.

The above data was collected from samples prepared using equipment configurations pertinent to lab conditions. Parameters can be obtained upon request by calling 800-706-1712.

(2) The data chart shows the R-value of this insulation. "R" means resistance to heat flow. The higher the R-value, the greater the insulating power. Compare insulation R-values before you buy. There are other factors to consider. The amount of insulation will depend upon the climate, the type and size of your house, and the fuel use patterns and family size. If you buy too much insulation it will cost you more than what you will save on fuel. To achieve proper R-values, it is essential that this insulation be installed properly.

(3) This numerical flame spread rating does not reflect hazards presented by this or any other material under actual fire conditions. Polyurethane foam systems should not be left exposed and must be protected by a minimum 15-minute thermal barrier or other code-compliant material as allowed by applicable building code(s) and Code Officials. Building Codes provide guidelines representing minimum requirements. Further information is available at www.iccsafe.org. Consult all Authorities Having Jurisdiction (AHJ) over an area for additional or specific requirements prior to beginning any project.

(4) ASTM E 84 is a test designed for sample thickness up to four (4) inches. NFPA 286 is a building code recognized alternative test conducted on large-scale assemblies to evaluate foam thickness in excess of four (4) inches as permitted in 2012 IBC Section 2603.10; 2006 & 2009 IBC Section 2603.9; 2009 & 2012 IRC Section R316.6; 2006 IRC Section R314.6.

(5) Using a conversion factor of 1 L/s* m² = 0.196850394 cfm/ft², the value <0.02 L/s*m² = <0.00393 cfm/ft²

SPRAYTITE® COMFORT XL SERIES BUILDING ENVELOPE INSULATION

GENERAL INFORMATION:

SPRAYTITE COMFORT XL is a spray polyurethane foam (SPF) system intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. BASF technical service personnel should be consulted in all cases where application conditions are questionable.

SPRAYTITE COMFORT XL has an estimated theoretical yield range of 5,000-5,500 board feet per set. Actual coverage can be in excess of or below the referenced estimated theoretical range based on factors affecting density including, however, not limited to: multiple lifts, substrate texture, substrate temperature, overspray loss, windy conditions, altitude, container residue, equipment characteristics & temperatures, applicator technique, etc. For help estimating yield for this and other spray foams, please consult Spray Polyurethane Foam Alliance's SPFA-121 SPF Estimating Reference Guide.

INSTALLATION CAUTIONS AND RECOMMENDATIONS:

SPRAYTITE COMFORT XL is designed for an application rate of a ½" minimum to a 6" maximum, with the optimal coverage for high lift applications at 5" to 6" inches thick. Dual lift application method (3.5"+3.5") with no dwell time between passes is a viable alternative. Installation in multiple, thinner passes could lead to increased density and reduced yield. Proper coating or dwell time is required between passes (minimum 10 minutes for every inch applied). Once installed material has cooled it is possible to add additional applications in order to increase the overall installed thickness of SPF. Be aware that passes exceeding 6.5" inches thick may develop high exothermic temperatures. Care should be taken to allow cooling of thick passes, and to avoid excess application thickness.

SPRAYTITE COMFORT XL is NOT designed for use as an EXTERIOR roofing system. BASF offers a separate line of products for exterior roofing applications. Cold-storage structures such as coolers and freezers demand special design considerations with regard to thermal insulation and moisture-vapor drive. SPRAYTITE COMFORT XL should NOT be installed in these types of constructions, unless the structure was designed by a design professional for specific use as cold storage. For more information please contact your sales or technical representative.

SPRAYTITE COMFORT XL is designed for installation to most standard construction materials such as wood, wood based products, plastics, metal and concrete. SPRAYTITE COMFORT XL has performed successfully when sprayed onto wood substrates down to 20°F using special cold weather application techniques. For heat sink-materials such as metal or concrete, SPRAYTITE COMFORT XL can be sprayed onto substrates down to 30°F, using a flash pass method. BASF recommends the use of mock ups or sample spray before starting the full-scale project. This will provide an opportunity to see how all materials are installed and evaluate their properties prior to proceeding. Please consult a BASF Representative for further information about applications using our liquid compounds.

Foam plastic materials installed in walls or ceilings may present a fire hazard unless protected by an approved, fire-resistant thermal barrier with a finish rating of not less than 15 minutes as required by building codes. Rim joists/header areas, in accordance with the IRC and IBC, may not require additional protection. Foam plastic must also be protected against ignition by code prescribed or properly tested materials in attics and crawl spaces. See relevant Building Codes and www.iccsafe.org for more information.

Important Material Preparation Note: Product should be stored at 50-80°F. Materials should be prepared for processing by being warmed to 70°F minimum at least 24 hours prior to installation and maintained at 70°F during the install process.

EQUIPMENT SETTING GUIDELINES– SPRAYTITE COMFORT XL		
Climate	A side, B side, Hose Temp (Adjust in +/- 5° increments)	Proportioner set pressure (Spraying pressure)
Colder	120°F – 140°F	1150 – 1450 psi (900 – 1200 psi)
Warmer	110°F – 125°F	1150 – 1450 psi (900 – 1200 psi)

BASF's SPF systems are formulated to produce foam with physical properties representative of our published data sheets within the factory set tolerances of commercially available fixed ratio proportioner units.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review related industry and best practice documents published by organizations such as Spray Polyurethane Foam Alliance (SPFA), OSHA, Spray Foam Coalition (SFC) and American Chemistry Council / Center for the Polyurethanes Industry (CPI)

As with all SPF systems improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials.

LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into an appropriate trash receptacle.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with or in close proximity to SPRAYTITE COMFORT XL or any polyurethane foam. Excessive pass thickness or limited dwell time between thick passes may result in scorch or fire risk – follow installation recommendations to avoid these issues. The insulation must not be used in areas that have a maximum service temperature greater than 180°F(82°C).

SHELF LIFE AND STORAGE CONDITIONS:

SPRAYTITE COMFORT XL has a shelf life of approximately six (6) months from the date of manufacture when stored in original, unopened containers at 50-80°F. As with all industrial chemicals this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY:

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use. We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages.

While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

"Warning" These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

Date: September 15, 2020

Page 2 of 2